

Free Questions for API-571 by certscare

Shared by Sutton on 22-07-2024

For More Free Questions and Preparation Resources

Check the Links on Last Page

Question Type: MultipleChoice

It is generally accepted that stresses approaching ______ are required for SCC to occur so that thermal stress relief is effective in preventing caustic SCC.

Options:			
A- MAWP			
B- Yield			
C- Creep range			
D- Critical			

Answer:

В

Question 2

Question Type: MultipleChoice

Options:

A- Decreases	
B- Increases	
C- Remains constant	
D- Varies	

Answer:

А

Question 3

Question Type: MultipleChoice

The dewpoint of hydrochloric acid depends on the concentration of hydrogen chloride. It is typically about ______.

Options:			
<mark>A-</mark> 180 F			
<mark>B-</mark> 160 F			
<mark>C-</mark> 130 F			
<mark>D-</mark> 110 F			

Answer:		
С		

Question Type: MultipleChoice

Stress relief and stabilization heat treatment of 300 Series SS for maximizing chloride SCC and PASCC resistance can cause ______ problems, especially in thicker sections.

Options:

A- Thermal fatigue

- **B-** Reheat cracking
- C- Hydrogen
- D- HIC

Answer:

В

Question 5

Question Type: MultipleChoice

Dissimilar weld metal cracking can be aggravated by _____.

Options:

A- Stress

B- Pressure

C- Thermal cycling

D- Cyclic stresses

С

Question 6

Question Type: MultipleChoice

Cracking susceptibility increases with _____ pH and carbonate concentration.

Options:			
A- Increasing			
B- Decreasing			
C- Low			
D- High			

Answer:

А

Question Type: MultipleChoice

Blistering, HIC, SOHIC and SSC damage can occur wherever there is a ______ environment.

Options:			
A- Wet HS			
B- Hydrogen			
C- Sulfur			
D- Aqueous			
Answer:			

А

Question 8

Question Type: MultipleChoice

Options:			
A- PWHT			
B- Preheat			
C- Temperature			
D- None of the above			

Answer:

А

Question 9

Question Type: MultipleChoice

SSC generally occurs below about _____.

Options:			
<mark>A-</mark> 225 F			
B- 200 F			
<mark>C-</mark> 180 F			
D- 150 F			

Answer:	
С	

Question Type: MultipleChoice

Blistering, HIC and SOHIC have been found to occur between ambient and _____.

Options:

A- 250 F

B- 300 F

C- 350 F

D- 400 F

Answer:

В

Question 11

Question Type: MultipleChoice

With sulfuric acid corrosion, carbon steel corrosion rates increases significantly if the flow velocity exceeds about _____m fps or at acid concentrations below ______.

Options:			
A- 6-9, 80%			
B- 5-7, 75%			
C- 2-3, 65%			

Answer: C

Question 12

Question Type: MultipleChoice

With sour water corrosion, at a given pressure, the HS concentration in the sour water ______ as temperatures ______.

Options:

- A- Increases, increases
- B- Decreases, decreases
- C- Increases, decreases
- D- Decreases, increases

Answer:

D

To Get Premium Files for API-571 Visit

https://www.p2pexams.com/products/api-571

For More Free Questions Visit

https://www.p2pexams.com/api/pdf/api-571

